

Comparative analysis of the skin decellularization methods

¹Olga Macagonova, ¹Doina Risnic, ²Adrian Cociug, ^{1,2}Viorel Nacu

¹Laboratory of Tissue Engineering and Cells Culture

Nicolae Testemitanu State University of Medicine and Pharmacy

²Human Tissue Bank, Orthopedic and Traumatological Hospital, Chisinau the Republic of Moldova

Authors' ORCID iDs, academic degrees and contributions are available at the end of the article

*Corresponding author: olga.macagonova@usmf.md

Manuscript received February 24, 2021; revised manuscript April 12, 2021; published online April 28, 2021

Abstract

Background: The extracellular matrix plays an important role in the promoting the tissue regeneration and repair. Decellularization or removal of the cells from the complex mixture of the structural and functional proteins that constitute the extracellular matrix (ECM) can be done by the physical (agitation, sonication, freeze and thaw), chemical (alkaline orchids, ionic detergents, nonionic, tri-n-butyl phosphate (TBP), hypotonic or hypertonic treatments, chelating agents), and enzymatic methods (trypsin or protease inhibitors). However, complications associated with the use of the decellularized skin have been reported, which are widespread and poorly understood. In this synthesis have been included publications, identified by the Google Search engine, National Bibliometric Tool (NBT), Pub Med databases, Web of Science, Springer, Elsevier, Wiley Online Library, Science Direct and Bioscience, Biotechnology and Biochemistry. The results of the decellularization were reported in terms of the number of cells remaining in the collagen fibers depending on the duration of exposure to chemical agents.

Conclusions: The natural matrix is more widely used than synthetic material, because it has the natural structure and composition of the ECM, it naturally stimulates cell development and allows the incorporation of the growth factors and other proteins increasing cell proliferation. The assessment of the quality of decellularization techniques is done by evaluating the necrosis of the extracellular matrix, the depletion of the collagen fibers and the remaining amount of genetic material.

Key words: decellularization, extracellular matrix, cell proliferation.

Cite this article

Macagonova O, Risnic D, Cociug A, Nacu V. Comparative analysis of the skin decellularization methods. *Mold Med J.* 2021;64(2):79-86. <https://doi.org/10.52418/moldovan-med-j.64-2.21.14>.

Introduction

The extracellular matrix plays an important role in the promoting of the tissue regeneration and repair [1]. With the development of the decellularization technology, the extracellular matrix in the form of a new biomaterial has attracted the attention of many researchers. The extracellular scaffold is the ideal substrate for the tissue engineering, presenting a carcass on which the body's cells survive [2, 3]. The functions of the extracellular matrix as a support material and biological substrate are the regulation of the cellular metabolism, such as the cell proliferation, morphogenesis and differentiation [4, 5]. Norton L. et al. described the decellularization technology of the use of the non-denaturing anionic detergent [2, 6]. The objectives of the decellularization process are to remove the potential immunogenic material and to obtain a biocompatible carcass for the growing cell host. Decellularization or removal of the cells from the complex mixture of the structural and functional proteins that make up the extracellular matrix can be done by the physical methods (agitation, sonication, freezing and thawing) [7, 8], chemical methods (alkaline oracids, ionic detergents, non-ionic, tri-n-butyl phosphate,

treatments with hypotonic, hypertonic substances [8], (EDTA) tetrasodium salt dihydrate chelating agents), enzymatic methods (trypsin) and protease inhibitors [9].

Following the decellularization of the skin, the remaining extracellular matrix is used in the tissue engineering [10], creating a skin graft used for the wound healing, the soft tissue reconstruction in the sports medicine [11–14]. Decellularized tissue samples are frequently used with a variety of the clinical applications. In the plastic surgery, the human acellular skin matrix was used for the tear duct repair [15–18], breast reconstruction [19–21], hernia repair [22–25], in the treatment of the chronic wounds, such as trophic ulcer of the diabetic foot [26–28]. With the development of the tissue engineering, the use of decellularized products is gradually expanding, as they can function as substitutes for the traditional biomaterials (e.g., polyurethanes, PLGA (poly (lactic-co-glycolic acid)), etc.) [29, 30]. Thus, they can serve as the inductive materials for the cell invasion. Therefore, the decellularization methods fall into three broad categories: physical, chemical and enzymatic [31, 32]. Most samples are prepared using a combination of the reagents, the most popular being chemical and enzymatic techniques [33, 34]. The effectiveness of the decellularization procedure

is characterized by the following parameters: the complete character of the removal of the cells and nuclear debris, the preservation of the matrix integrity, the tissue density and the ability of the cell repopulation. The decellularized matrix must be compatible for the cells and have a repairing phenotypic building material [35]. Natural scaffolding allows the invasion, proliferation and proper secretion of the cells, which is important for their survival and regeneration of the affected tissue [36–41]. The shortcomings of some decellularization methods are: the persistence of the residual deoxyribonucleic acid (DNA), which has a significant proinflammatory effect [37], inhibitory response on the cell proliferation and the cytotoxic effect [38, 40]. Researchers have described the factors that can lead to these negative effects on the matrix, being the residual detergents, sterilizing chemicals that change the structure of the scaffold [42]. The material was synthesized based on the randomized studies, clinical and preclinical experimental cases, published between 2003 and 2020, which aimed to elucidate the results of the skin decellularization. In this synthesis, the publications accessible in English, identified by the Google Search engine, National Bibliometric Tool, Pub Med databases, Web of Science, Springer, Elsevier, Wiley Online Library, Science Direct and Bioscience, Biotechnology and Biochemistry, from the databases of the life science journals and online books by the keywords are exposed in the table 1.

The literature synthesis was performed using 61 sources from PubMed, 11 – through the National Biometric Tool, 5 – Springer, 2 from ScienceDirect, 2 – Web of Science, 1 from Bioscience, Biotechnology and Biochemistry, 1 – Wiley Online Library and 1 from Elsevier.

For the advanced selection of the bibliographic sources, the following filters were applied: papers published until September 2020, articles in Romanian and English. Original research journals were selected informing about studies, conducted in the clinical, preclinical and experimental conditions. After examining the titles of the articles obtained, only works containing relevant information on the skin decellularization methods were selected. The bibliography of the selected articles was also studied, in order to find all potentially significant sources of the intended purpose. The information was systematized, highlighting the main aspects of the contemporary vision on the obtaining of the

extracellular dermal matrix. If necessary, the additional sources of the information were consulted to clarify some notions. Duplicate publications, articles that did not correspond to the purpose of the paper and were not accessible for viewing, were excluded from the list of the publications generated by the Search engine.

The evaluation of the decellularization of the biological scaffold for the tissue engineering was based on the cellularity of the matrix [43]. The studies were performed on the fragments of the rat, pig and human skin, taken from the back and abdomen in the first 24 hours after the euthanasia of the animals or the death of the donor. Prior to processing, in order to wash the tissue of impurities, the skin was stored in cold phosphate buffer (PBS) with antibiotic (0.1% Amikacin). Thereafter, the skin was rinsed with PBS to remove the blood residue. The maximum time between the skin sampling and tissue decellularization initiation was up to 4 hours. Deepithelated skin can be obtained by different methods: the mechanical removal of the epidermis [44], osmotic method, enzymatic method with trypsin (0.5%) and 2M sodium chloride [45, 46]. All decellularization reagents were evaluated by point of view of the mechanism of the action and the effect on the extracellular matrix [2, 44, 47]. The isolated material was characterized by the histological examination by eosin and hematoxylin staining, Massom trichrome and spectrophotometric quantification of the nucleic residue.

There are the different reagents and techniques (chemical, physical and enzymatic) of the skin decellularization and usually these methods are used in the combination to increase the effectiveness of the decellularization process. A dermal matrix is made using a three-step method. First, the epidermis is removed using a chemical process. The next decellularization process consisting of the breaking of the lipid-lipid, lipid-protein bonds, solubilization of the cell membranes, osmotic lysis of cells, dehydrating and rupture of the cell membrane finally to varying degrees, will dissociate DNA. The last one, a subsequent washing will remove any residual cellular elements or chemicals [48].

Kumar N. et al. [44] developed the successful techniques for the deepithelialization of the skin by the hypertonic solution. The composition of the substances dissolved in 100 ml of the phosphate buffer solution was as follows: 605 mg of tris base, 4 grams of sodium chloride, 202.5 mg of

Table 1. Search engines and the keywords used in the synthesis

Key words	NBT	PubMed	Web of science	Elsevier	Springer	Wiley Online Library	BBB	Science Direct
skin biomaterials	23	7468	84	2482	3518	4	20	28766
skin tissue engineering	48	479	2752	17308	40967	465	49	77409
decellularization	8	1873	1697	1900	20	2624	4	5894
skin DNA	2	57	569	1826	9	611	193	250463
ECM	32	27909	1256	107	130	51386	495	652
skin	634	791091	2200	1826	2562	1706	938	100000+
skin cellularity	2	864	77	5118	2717	6	214	332168

EDTA. The skin was washed on an orbital shaker at 37° C for 8 hours at 150 rpm. The solution was changed every 4 hours. Macroscopic and microscopic examination was performed at intervals of 4 and 8 hours [44].

Obtaining of the qualitative matrix required the combination of the reagents or the independent action of ones: 1) 0.5% sodium dodecyl sulfate (SDS) with 0.1% EDTA [3]; 2) trypsin combined with EDTA assisted of 1% triton X-100 and 0.26% tris (2-Amino-2-(hydroxymethyl)-1.3-propanediol) [46]; 3) hypertonic solution with 2-Amino-2-(hydroxymethyl)-1.3-propanediol (tris), sodium chloride and EDTA; 4) 1% triton X-100 combined with 0.25% TBP; 5) 0.5% sodium dodecyl sulfate (SDS) with 0.25% tri-n-butyl phosphate; 6) 1% or 2% sodium deoxycholate (SD) followed by the action of the deoxiribonuclease [44]; 7) hypertonic solution of 1M sodium hydroxide (NaOH) perfects the decellularization action of the 0.25% trypsin – EDTA solution [47]; 8) freeze-thaw cycling (-80°C, six times) with ammonia water (25 mM); 9) 0.1% triton X-100 with 1.5M K Cl aqueous solution; 10) freeze-thaw cycling alone; 11) ammonia water alone; 12) triton X-100 extraction; 13) osmotic shock with 1.5M K Cl; and 14) and freeze-thaw cycling with 3M NaCl [49].

All reagents were helped by the continuous agitation at the room temperature or 37° C in a thermostat for 24 and 48 hours on an orbital shaker at 150 rpm. The solutions were changed at different intervals of 6, 12, 24 and 48 hours. Finally, the tissues were rinsed thoroughly several times with sterile buffer or the distilled water on the orbital shaker. Macroscopic and microscopic examinations were performed at 12 and 48 hours.

Results and discussion

As a result of the processing of the information identified by Google Search engine, National Bibliometric Tool, Pub Med databases, Web of Science, Springer, Elsevier, Wiley Online Library, Science Direct and Bioscience, Biotechnology and Biochemistry, from the databases of the life science journals and online books according to the search criteria 879664 articles were found that address the issue of the skin decellularization. After the primary analysis of the titles, 201 articles were qualified as possibly relevant for the

given synthesis. After their repeated review, 84 publications relevant to the stated purpose were finally selected.

As a result of the systematization of the literature data, it was highlighted that the normal structure of the skin served as a template after which the decellularized sample was evaluated according to twenty-one decellularization methods compared for their decellularization effects during skin scaffold preparation (table 2). The authors described the thick epidermis followed by the cellular dermal matrix. Masson trichrome staining showed a preserved cell epidermis, the dermis – with an abundance of the collagen fibers [44].

The final bibliography of the paper included 84 publications. As a result these methods were combined in fourteen separate decellularization protocols [2, 44–47, 49].

The macroscopic estimation of the deepithelialized rat skin with the hypertonic solution for an interval of 4 hours found that the epidermis was not separated from the dermis. Thus, after 6 hours the multilayered epithelium was removed more easily. However, after another 8 hours the epidermis was spontaneously separated with minimal mechanical effort and resulted in an incompletely epithelialized dermal matrix [47].

In this study, twenty-one decellularization methods were evaluated by which the incomplete acellular dermis was obtained (table 2). The treatment of the skin with the hypertonic saline after 24 hours resulted the cell-less matrix with collagen fibers with insignificant thickness. The deepithelialized skin treated with triton X-100 was characterized by more significant cell-less and with the thick collagen fibers. There were cell debris between the interstitial spaces of the collagen fibers [47]. At 48 hours, the complete acellular dermis with increased porosity was described. The treatment of the skin by SDS over 24 hours showed the cell-less membrane with the collagen fibers with the significantly preserved thickness [2]. At 48 hours, the collagen fibers were more fragile with large spaces between them. Treatment with 1% SD effectively removed the cell debris at 48 hours. Increasing of the concentration from 1% to 2% of SD, led to the expansion of the spaces between the collagen fibers. No cell nuclei were observed, and the tissue was composed of the extracellular matrix. At 48 hours,

Table 2. Overview of the techniques used in the skin decellularization

Methods	Mechanism	The effect on ECM	References
Chemical			
Alkaline and acids: ammonium hydroxide, hydrochloric acid, sulfuric acid	Solubilizes the cytoplasmic components of cells; disrupts nucleic acids	Eliminate glycosaminoglycans (GAGs), Dissociates GAGs from collagenous tissues	[50–52]
Peracetic acid	More effectively disrupts cell membranes	Preserves many of the native GAGs, preserves the structure and function of many growth factors that are resident in the ecm, including transforming growth factor-β, essential fibroblast growth factor and vascular endothelial growth factor, highly efficient in removing cellular material	[53, 54]

Non-ionic detergents			
Triton-X-100	Breaks the lipid-lipid and lipid-protein bonds, leaving the protein-protein bonds intact	Almost completely eliminates GAGs, reduced the laminin and fibronectin content	[50–52]
Ionic detergents			
Sodium duodecyl sulfate (SDS)	Solubilizes cytoplasmic and nuclear cell membranes	Removes nuclear debris and cytoplasmic proteins (vimentin); tends to disrupt the structure of the native tissue, reduced concentrations of GAG and loss of the collagen integrity	[50–52]
TBP	Tend to distort proteins	Keep resistance of of the collagen fibers, but reduce in the collagen content More effective than detergents such as Triton X-100 and sodium dodecyl sulfate (SDS), with varying effects on the preservation of ECM constituents and its native mechanical properties	[55]
Sodium deoxycholate	Solubilizes the cell and cytoplasmic membranes	Disrupts ECM components more strongly than SDS	[56]
Hypotonic and hypertonic solutions	Cell lysis by osmotic shock	Effective for cell lysis, but do not effectively remove cell debris	[50–52]
EDTA	Chelating agents that bind divalent metal ions, thereby disrupting cell adhesion to ECM	Relatively reduce the cellularity of the ECM	[57]
Solvents			
Alcohol	Dehydrating and lysing of the cells during tissue decellularization	Decreases levels of structural proteins involved in the interstitial matrix and basement membrane, with a concomitant increase in proteolytic enzymes that degrade these components	[58–60]
Glycerol	Dehydrating and lysing of the cells during tissue decellularization	Collagen fiber reassembly, increases the tissue transparency	[61]
Acetone	Removes lipids during decellularization	Damages the ECM ultrastructure	[62, 63]
Enzymatic			
Trypsin	Removes the peptide bonds of arginine and lysine	Disruption of the ECM, prolonged exposure eliminates laminin, fibronectin, elastin and GAGs, does not influence the amount of collagen in the tissue, decreases tensile strength of the collagen fibres	[50–52]
Endonuclease	Cleaves phosphodiester bonds within a ribonucleotide and deoxyribonucleotide chains	Difficult to remove from tissue and can invoke an immune response	[50–52]
Exonuclease	Cleaves nucleotides from the end of a nucleic acid chain	Slightly reduces ECM cellularity	[52]
Dispase	Cleaves specific peptides, especially collagen IV and fibronectin	Slightly reduces ECM cellularity	[64]
Phospholipase A2	Hydrolyzes the phospholipid component	Catalyzes the release of arachidonic acid in the cells, phospholipase A2 -arachidonic acid system is involved in the matrix-initiated signal transduction pathway in ECM, stimulates the ECM cell proliferation by homologous lectin	[58]
Physical			
Freezing	Intracellular ice crystals disrupt the cell membrane	Relative ECM disturbance	[59, 60, 51]
Freeze–thaw cycling	Cell lysis	Freeze–thaw cycling alone could not remove all the cell nuclei	[49]
Pressure	Rupture of the cell membrane	Relative disturbance of ECM	[65]
Agitation	It is used to facilitate chemical exposure and removal of cellular material	Aggressive agitation or sonication may disrupt ECM	[66]
Electroporation	The oscillation of the electric field disturbs the cell membrane	Partial cell membrane lysis	[49]

all samples treated according to the protocols showed the complete cell-less matrix with the removal of the cellular debris from the tissue [64].

The hypotonic and hypertonic solutions have been reported as the ineffective decellularizing agents [64–66]. They caused the cell lysis but did not remove the cell debris from tissues [64]. TBP treatment has led to a complete removal of the nuclear waste. TBP did not affect the resistance of the collagen fibers but led to decrease the GAGs content [67].

The cellular content of ECM has the potential to cause rejection when is grafted, therefore it must be removed before the transplantation. DNA and Gal-epitope are two main reasons why the host can respond. The epitope Gal, the α -Gal oligosaccharide (Gal α 1.3-Gal β 1–4GlcNAc-R), is a membrane antigen present in all species, except for Old World monkeys and humans. The absence of α -gal expression in the humans and non-human primates is related to the defects in the α 1.3-galactosyl-transferase gene, which catalyzes the assembly of the α -gal molecule in other animals [68]. Because humanity does not have this antigen, transplanting a xenograft leads to a host reaction, causing the graft to be rejected. Therefore, the Gal epitope must be removed from the xenografts before being transplanted [31]. Because the DNA left in the graft can cause inflammatory reactions in the host it must be removed during decellularization. Another reason why DNA needs to be removed is that it causes calcification after implantation. However, because most tissues are very dense, DNA is almost impossible to be 100% removed. Therefore, DNA remaining after the decellularization should be examined quantitatively or qualitatively, that is no image should be obtained after the staining with 4',6-diamidino-2-phenylindole (DAPI) or hematoxylin and eosin (H&E) [42, 69].

Criteria for the assessing the effectiveness of the removal of these components are suggested as follows: Decellularized ECM must have (1) less than 50 ng double-stranded DNA per mg dry weight, (2) less than 200 bp DNA length fragment and (3) no nuclear material visible by 4', 6-diamidino-2-phenylindole or hematoxylin and eosin staining [70]. In addition, the protein content remaining in the ECM must be assessed, focusing on structural proteins, such as collagen, fibronectin, laminin, GAGs and growth factors. Furthermore, the mechanical properties, including elastic recoil and tensile strength, depending on the application, must match the original tissue. In this review, decellularization techniques are evaluated for their effectiveness in these four areas, to rule out failure of complete tissue decellularization, leading to negative results after *in vivo* implantation, including a pro-inflammatory response with M1 macrophage recruitment and subsequent fibrosis [71].

The most decellularization efficacy test reports revealed positive the data on X-100 triton treatment compared to 0.1% SDS and 0.1% trypsin solutions [72–76]. Woods T. and co-authors demonstrated that the X-100 triton decellularization method in the combination with SDS or tri-n-butyl phosphate solution was the most effective, but also the most destructive in terms of the depletion of glycosaminoglycan

and collagen [66]. This phenomenon was also shown in the study of Purohit S. [45] who decellularized the skin with trypsin, triton and sodium hydroxide and observed the fibrinoid necrosis, fragmentation and undulation of the fibrillar structures in the dermis which states the depletion of the dermal matrix. Although, from the protocols tested in the study [77], triton X-100 had the least harmful effect on the content of glycosaminoglycans. Crapo P. et al. [69, 78] have suggested that the denser tissues, such as the dermis, tendon and trachea require the decellularization protocols by the continuous agitation, which last from days to months. However, in the present study, the desired results were obtained after 48 hours of the treatment with the biological detergents.

Badylak S. and Gilbert T. [31] have shown that cells and cellular products cannot be completely removed from dense tissues, such as the dermis, even with the most rigorous processing methods. However, in the present study, the complete cell-less membrane was observed after 48 hours of the treatment, although SDS solubilized the cell membranes and dissociated DNA. Therefore, it is effective in the removing of the cellular material from the tissues. Sodium dodecyl sulfate has been more effective in the removing of the cell residues and cytoplasmic proteins such as vimentin from the tissue compared to other detergents, but is more aggressive for ECM [79, 80]. Dodecyl sulfate was more effective than Triton-X 100 in the removing of the nuclei from the dense tissues. SDS disrupted the native tissues and caused a decrease of GAG concentration and depleted collagen [9]. SD is very effective for the removing cellular debris. SD has been shown not to alter the structural properties of the ECM structure, as observed in Kasimir M's study [70] but tends to disrupt the structure of the tissue itself, so it should be used in a lower concentration.

Among the methods described by Hongxu Lu et al., the methods of freeze-thaw cycling with NH(4) OH and triton X-100 with 1.5M K Cl showed the best effect on the removal of cellular components from the complexes, while the other five methods could only partially remove cellular components. The ECM scaffolds prepared by these two methods had similar gross appearances and microstructures [49].

Qi Xing et al. investigated three decellularization methods: high concentration (0.5wt.%) of sodium dodecyl sulfate (SDS), low concentration (0.05wt.%) of SDS, and freeze-thaw cycling method. They found that the high SDS treatment could efficiently remove around 90% of DNA from the cell sheet, but significantly compromised their ECM content and mechanical strength. The elastic and viscous modulus of the ECM decreased around 80% and 62%, respectively, after the high SDS treatment. The freeze-thaw cycling method maintained the ECM structure as well as the mechanical strength, but also preserved a large amount of the cellular components in the ECM scaffold. Around 88% of DNA was left in the ECM after the freeze-thaw treatment. *In vitro* inflammatory tests suggested that the amount of DNA fragments in ECM scaffolds does not cause a significantly different immune response. All three

ECM scaffolds showed comparable ability to support *in vitro* cell repopulation [63, 81].

Haozhen R. et al. described the successful results if the decellularization after the treatment with SDS and Triton X-100. The total absence of the nuclear structures and removal of viable cells were confirmed by hematoxylin-eosin staining and scanning electron microscopy. Collagen was preserved after both treatments. However, the elastin content decreased to about 20% and 60%, the GAGs content decreased to about 10% and 50% and the HGF content decreased to about 20% and 60% of the native liver level after SDS and Triton X-100 treatment respectively. The Triton X-100-treated scaffolds were much superior to SDS-treated scaffolds in the supporting liver-specific function, including albumin secretion ($P=0.001$), urea synthesis ($P=0.002$), ammonia elimination ($P=0.007$) and mRNA expression levels of the drug metabolism enzymes [82–84].

However, there are studies [55–61], that the enzymatic removal of epitopes from the cell surface reduces the immunogenicity of the xenograft. Thus, in the research [47–55], it has been shown that the presence of the cells in the interstitium and their necrosis after the transplantation can delay the infiltration of the host cells that affect the regeneration. It is obvious, that the specifics of the interaction between the matrix and the cells of the recipient remain to be addressed in the following researches.

Conclusions

1. The removal of the cells, proteins, DNA from the skin and the porosity of the samples, directly correlate with the exposure time in the decellularization solution.

2. The highest quality extracellular matrices were prepared using a combination of chemical and enzymatic methods.

3. It is clear that skin decellularization with sodium dodecyl sulfate was the most successful and safe method in terms of minimizing the amount of DNA and the risks of the graft rejection after the transplantation.

4. Probably the pig skin could be considered as a study substrat, being available and easily processable, taking into consideration ethical aspects and grafts safety.

5. It has been found that the tissue decellularization probably inhibits the subsequent proliferation of the fibroblasts in the matrix, this fact requires further research.

6. The natural matrix is more widely used than synthetic material, because it has the natural structure and composition of the ECM, it naturally stimulates cell development and allows the incorporation of the growth factors and other proteins increasing cell proliferation. The assessment of the quality of decellularization techniques is done by evaluating the necrosis of the extracellular matrix, the depletion of the collagen fibers and the remaining amount of genetic material.

References

1. Malcova T, Globa, L, Vascan A, Ţugui E, Stoian A, Nacu V. Mechanical and morphological characterization of decellularized umbilical vessels as tissue engineering scaffolds. In: Tiginianu I, Sontea V, Railean S, edi-

- tors. 4th International Conference on Nanotechnologies and Biomedical Engineering: IFMBE Proceedings. Vol. 77. Cham: Springer; 2019. p. 589–594. https://doi.org/10.1007/978-3-030-31866-6_105.
2. Timbalari T. Estimating the clinical needs for tissues and cells in the Republic of Moldova. *Mold Med J.* 2020;63(1):19–25. doi: 10.5281/zenodo.3685656.
3. Cirimpei O, Malcova T, Cirimpei D, Nacu V. Substituenții biologici ai pielii – între mit și realitate = Biological substitutes for the skin – between myth and reality. *Mold J Health Sci.* 2016;1(7):88–102. Romanian, English.
4. Cebotari S, Tudorache I, Jaekel T, et al. Detergent decellularization of heart valves for tissue engineering: toxicological effects of residual detergents on human endothelial cells. *Artif Organs.* 2010;34(3):206–210. doi: 10.1111/j.1525-1594.2009.00796.x.
5. Jian M, Cobzac V, Moghildea I, Macagonova O. The three-dimensional liver matrix for tissue engineering. In: *MedEspera 2018: 7th International medical congress for students and young doctors; 2018 May 3–5; Chisinau, the Republic of Moldova.* Chisinau; 2018. p. 201–202.
6. Norton L, Babensee J. Innate and adaptive immune responses in tissue engineering. In: Meyer U, Handschel J, Wiesmann H, Meyer T, editors. *Fundamentals of tissue engineering and regenerative medicine.* Berlin: Springer; 2009. p. 721–745. https://doi.org/10.1007/978-3-540-77755-7_50
7. Meyer S, Chiu B, Churchill T, et al. Comparison of aortic valve allograft decellularization technique in rats. *J Biomed Mater Res A.* 2006; 79(2):254–262. doi: 10.1002/jbm.a.30777.
8. Won JY, Lee MH, Kim MJ, et al. A potential dermal substitute using decellularized dermis extracellular matrix derived bio-ink. *Artif Cells Nanomed Biotechnol.* 2019;47(1):644–649. doi: 10.1080/21691401.2019.1575842.
9. Jian M, Cobzac V. Obtaining a suitable osteochondral graft for articular cartilage engineering. In: *MedEspera 2018: 7th International medical congress for students and young doctors; 2018 Mai 3–5; Chisinau, the Republic of Moldova.* Chisinau; 2018. p. 202.
10. Jian M, Cobzac V, Moghildea I, Popescu V, Nacu V. Techniques of liver decellularization. *Mold Med J.* 2018;61(4):21–24. doi: 10.5281/zenodo.2222303.
11. Pellegata A, Asnaghi M, Stefani I, et al. Detergent-enzymatic decellularization of swine blood vessels: insight on mechanical properties for vascular tissue engineering. *Biomed Res Int.* 2013;2013:918753. doi: 10.1155/2013/918753.
12. Wilkins R. Acellular dermal graft augmentation in quadriceps tendon rupture repair. *Curr Orthop Pract.* 2010;21(3):315–319. doi: 10.1097/bco.0b013e3181c7ea2e.
13. Cobzac V, Coşciug S, Jian M, Nacu V. Appreciation of cartilage permeability within demineralized and decellularized osteochondral allogeneic graft with trypan blue. In: *Current issues of traumatology and osteosynthesis: Materials of the scientific-practical conference with International participation; 2017 Apr 27–28; Chernivtsi, Ukraine.* p. 140.
14. Cobzac V, Verestiuc L, Jian M, Nacu V. Assessment of ionic and anionic surfactants effect on demineralized osteochondral tissue. In: *IOP Conference Series: Materials Science and Engineering. International Conference on Innovative Research; 2019 May 16–17. Iasi, Romania.* Vol. 572:012084. doi: 10.1088/1757-899X/572/1/012084.
15. Wong I, Burns J, Snyder S. Arthroscopic Graft-Jacket repair of rotator cuff tears. *J Shoulder Elbow Surg.* 2010;19(2 Suppl):104–109. doi: 10.1016/j.jse.2009.12.017.
16. Pavlovski E, Stoian A, Iordăchescu R, Malcov T, Verega G, Nacu V. Combined decellularization of vascularized bone allograft. *In vivo experimental study stage.* In: *The Congress of Nicolae Testemițanu State University of Medicine and Pharmacy dedicated to the 75th anniversary: Abstract book; 2020 Oct 21–23; Chisinau, the Republic of Moldova.* p. 519.
17. Bond J, Dopirak R, Higgins J, et al. Arthroscopic replacement of massive, irreparable rotator cuff tears using a Graft-Jacket allograft: technique and preliminary results. *Arthroscopy.* 2008;24(4):403–409. doi: 10.1016/j.arthro.2007.07.033.
18. Dopirak R, Bond J, Snyder S. Arthroscopic total rotator cuff replacement with an acellular human dermal allograft matrix. *Int J Shoulder Surg.* 2007;1:7–15. doi: 10.4103/0973-6042.30673.

19. Sbitany H, Sandeen S, Amalfi A, et al. Acellular dermis-assisted prosthetic breast reconstruction versus complete submuscular coverage: a head-to-head comparison of outcomes. *Plast Reconstr Surg.* 2009;124(6):1735-1740. doi: 10.1097/prs.0b013e3181bf803d.
20. Nahabedian M. AlloDerm performance in the setting of prosthetic breast surgery, infection, and irradiation. *Plast Reconstr Surg.* 2009;124(6):1743-1753. doi: 10.1097/PRS.0b013e3181e60652.
21. Salzberg A. Nonexpansive immediate breast reconstruction using human acellular tissue matrix graft (AlloDerm). *Ann Plast Surg.* 2006;57(1):1-5. doi: 10.1097/01.sap.0000214873.13102.9f.
22. Kapfer S, Keshen T. The use of human acellular dermis in the operative management of giant omphalocele. *J Pediatr Surg.* 2006;41(1):216-220. doi: 10.1016/j.jpedsurg.2005.10.093.
23. Albo D, Awad S, Berger D, et al. Decellularized human cadaveric dermis provides a safe alternative for primary inguinal hernia repair in contaminated surgical fields. *Am J Surg.* 2006;192(5):e12-17. doi: 10.1016/j.amjsurg.2006.08.029.
24. Candage R, Jones K, Luchette F, et al. Use of human acellular dermal matrix for hernia repair: friend or foe? *Surgery.* 2008;144(4):703-711. doi: 10.1016/j.surg.2008.06.018.
25. Mitchel LC, Cima R. A novel technique for the repair of urostomal hernias using human acellular dermal matrix. *Urology.* 2011;77(3):746-750. doi: 10.1016/j.urology.2010.05.003.
26. Winters C, Brigido S, Liden B, Simmons M, et al. A multicenter study involving the use of a human acellular dermal regenerative tissue matrix for the treatment of diabetic lower extremity wounds. *Adv Skin Wound Care.* 2008;21(8):375-381. doi: 10.1097/01.ASW.0000323532.98003.26.
27. Malcova T, Băluțel T, Cociug A, Popescu V, Nacu V. Tissue engineered vascular grafts: decellularization of porcine aorta through three different methods. In: *MedEspera 2020: 8th International medical congress for students and young doctors; 2020 Sep 24-26; Republic of Moldova. Chisinau; 2020.* p. 101.
28. Brown B, Badylak S. Extracellular matrix as an inductive scaffold for functional tissue reconstruction. *Transl Res.* 2014;163:268-285. doi: 10.1016/j.trsl.2013.11.003.
29. Nacu V, Jian M, Moghildea I, Cobzac V, Nacu L, Popescu V. Liver matrix obtained by decellularization procedure. In: *TERMIS World Congress; 2018 Sep 4-7; Kyoto, Japan. Springer; 2018.* p. 2.
30. Andre E B, Bela K, Horvath T, et al. Successful re-endothelialization of a perfusable biological vascularized matrix (BioVaM) for the generation of 3D artificial cardiac tissue. *Basic Res Cardiol.* 2014;109(6):441. doi: 10.1007/s00395-014-0441-x.
31. Badylak S, Gilbert T. Immune response to biologic scaffold materials. *Semin Immunol.* 2008;20(2):109-116. doi: 10.1016/j.smim.2007.11.003.
32. Böer, U, Lohrenz A, Klingenberg M, et al. The effect of detergent-based decellularization procedures on cellular proteins and immunogenicity in equine carotid artery grafts. *Biomaterials.* 2011;32(36):9730-9737. doi: 10.1016/j.biomaterials.2011.09.015.
33. Naso F, Aguiari P, Iop L, Spina M, Gerosa G. Biocompatibility evaluation criteria for novel xenograft materials: distribution and quantification of remnant nucleic acid and alpha-Gal epitope. *J Stem Cell Res Ther.* 2013;S6:009. doi: 10.4172/2157-7633.s6-009.
34. Nacu V, Cobzac V, Jian M, Verestiuc L. Decellularized-demineralized osteochondral allografts testing on rabbit model. Preliminary report. In: *TERMIS World Congress; 2018 Sep 4-7; Kyoto, Japan. Springer; 2018.* p. 140.
35. Belviso I, Romano V, Sacco A. Decellularized human dermal matrix as a biological scaffold for cardiac repair and regeneration. *Front Bioeng Biotechnol.* 2020;8:229. <https://doi.org/10.3389/fbioe.2020.00229>.
36. Chou P, Lin Y, Wu SH, et al. Supercritical carbon dioxide-decellularized porcine acellular dermal matrix combined with autologous adipose-derived stem cells: its role in accelerated diabetic wound healing. *Int J Med Sci.* 2020;17(3):354-367. doi: 10.7150/ijms.41155.
37. Dong S, Ying D, Duan X, et al. Bone regeneration using an acellular extracellular matrix and bone marrow mesenchymal stem cells expressing Cbfa1. *Biosci Biotechnol Biochem.* 2009;73(10):2226-2233. doi: 10.1271/bbb.90329.
38. Cobzac V, Mostovei A, Jian M, Nacu V. An efficient procedure of isolation, cultivation and identification of bone marrow mesenchymal stem cells. *Mold Med J.* 2019;62(1):35-41. doi: 10.5281/zenodo.2590011.
39. Gilbert T, Sellaro T, Badylak S. Decellularization of tissues and organs. *Biomaterials.* 2006;27(19):3675-3683. doi: 10.1016/j.biomaterials.2006.02.014.
40. Gratzner P, Harrison R, Woods T. Matrix alteration and not residual sodium dodecyl sulfate cytotoxicity affects the cellular repopulation of a decellularized matrix. *Tissue Eng.* 2006;12(10):2975-2983. doi: 10.1089/ten.2006.12.2975.
41. Eremia V, Babuci S, Petrovici V, Negru I, Nacu V, Cobzac V. Reconstrucția chirurgicală experimentală a defectelor diafragmatice prin utilizarea grefelor biologice decelularizate. Rezultate preliminare [Preliminary results in evaluation of decellular biological materials used in experimental surgical reconstruction of diaphragmatic defects]. *Arta Medica (Chisinau).* 2018;(3/68):4-8. Romanian.
42. Keane T, Londono R, Turner N, et al. Consequences of ineffective decellularization of biologic scaffolds on the host response. *Biomaterials.* 2012;33:1771-1781. doi: 10.1016/j.biomaterials.2011.10.054.
43. Goncalves A, Griffiths L, Anthony R, et al. Decellularization of bovine pericardium for tissue engineering by targeted removal of xenoantigens. *J Heart Valve Dis.* 2005;14(2):212-217.
44. Kumar N, Gangwar A, Sharma A, et al. Extraction techniques for the decellularization of rat dermal constructs. *Trends Biomater Artif Organs.* 2013;27(3):102-107.
45. Purohit S. Biocompatibility testing of acellular dermal grafts in a rabbit model: an *in-vitro* and *in-vivo* study [dissertation]. Itanagar: Deemed University; 2008. p. 243-244.
46. Reing J, Brown B, Daly K, et al. The effects of processing methods upon mechanical and biologic properties of porcine dermal extracellular matrix scaffolds. *Biomaterials.* 2010;31(33):8626-8633. doi: 10.1016/j.biomaterials.2010.07.083.
47. Zhao Y, Zhang Z, Wang J, et al. Abdominal hernia repair with a decellularized dermal scaffold seeded with autologous bone marrow-derived mesenchymal stem cells. *Artif Organs.* 2012;36(3):247-255. doi: 10.1111/j.1525-1594.2011.01343.
48. Gupta S, Mishra N, Dhasmana A. Decellularized scaffolds and organogenesis. Decellularization methods for scaffold fabrication. *Methods Mol Biol.* 2018;1577:1-10. doi: 10.1007/978-1-4939-9434-3_34.
49. Lu H, Hoshiba T, Kawazoe N, Chen G. Comparison of decellularization techniques for preparation of extracellular matrix scaffolds derived from three-dimensional cell culture. *J Biomed Mater Res A.* 2012;100(9):2507-16. doi: 10.1002/jbm.a.34150.
50. Fu RH, Wang YC, Liu SP, et al. Decellularization and recellularization technologies in tissue engineering. *Cell Transplant.* 2014;23(4-5):621-630. doi: 10.3727/096368914X678382.
51. Sicari B, Londono R, Badylak S. Extracellular matrix as a bioscaffold for tissue engineering. In: *Blitterswi Clemens A van, Boer Jan de, editors. Tissue Engineering. 2nd ed. Amsterdam: Elsevier; 2014.* p. 149-175.
52. Lopresti S, Brown B. Host response to naturally derived biomaterials. In: *Badylak S, editor. Host response to biomaterials. Vol. 4. Elsevier; 2015.* p. 53-79.
53. Cartmell J, Dunn M. Effect of chemical treatments on tendon cellularity and mechanical properties. *J Biomed Mater Res.* 2000;49(1):134-140. [https://doi.org/10.1002/\(SICI\)1097-4636\(200001\)49:1<134::AID-JBM17>3.0.CO;2-D](https://doi.org/10.1002/(SICI)1097-4636(200001)49:1<134::AID-JBM17>3.0.CO;2-D).
54. Deeken C, White A, Bachman S, et al. Method of preparing a decellularized porcine tendon using tributyl phosphate. *J Biomed Mater Res B Appl Biomater.* 2011;96(2):199-206. doi: 10.1002/jbm.b.31753.
55. Yang B, Zhang Y, Zhou L, et al. Development of a porcine bladder acellular matrix with well-preserved extracellular bioactive factors for tissue engineering. *Tissue Eng Part C Methods.* 2010;16(5):1201-1211. doi: 10.1089/ten.TEC.2009.0311.
56. Prasertsung I, Kanokpanont S, Bunaprasert T, et al. Development of acellular dermis from porcine skin using periodic pressurized technique. *J Biomed Mater Res B Appl Biomater.* 2008;85(1):210-219. doi: 10.1002/jbm.b.30938.
57. Lumpkins S, Pierre N, McFetridge P. A mechanical evaluation of three decellularization methods in the design of a xenogeneic scaffold for tissue engineering the temporomandibular joint disc. *Acta Biomater.* 2008;4(4):808-816. doi: 10.1016/j.actbio.2008.01.016.
58. Liu Y, Bharadwaj S, Lee S J. Optimization of a natural collagen scaffold to aid cell-matrix penetration for urologic tissue engineering. *Biomaterials.* 2009;30(23-24):3865-3873. doi: 10.1016/j.biomaterials.2009.04.008.

59. Hodde J, Badylak S, Brightman A, et al. Glycosaminoglycan content of small intestinal submucosa: a bioscaffold for tissue replacement. *Tissue Eng.* 1996;2(3):209-217. doi: 10.1089/ten.1996.2.209.
60. Hodde J, Record R, Liang H, et al. Vascular endothelial growth factor in porcine-derived extracellular matrix. *Endothelium.* 2001;8(1):11-24. doi: 10.3109/10623320109063154.
61. Voytik-Harbin S, Brightman A, Kraine M, et al. Identification of extractable growth factors from small intestinal submucosa. *J Cell Biochem.* 1997 Dec 15;67(4):478-91.
62. Ott H, Rajab T. Biological methods to decellularize tissues. In: *In Situ Tissue Regeneration.* Elsevier; 2016 [cited 2020 Sep 12]. Available from: <https://www.sciencedirect.com/topics/engineering/decellularization>
63. Xing Q, Yates K, Tahtinen M, et al. Decellularization of fibroblast cell sheets for natural extracellular matrix scaffold preparation. *Tissue Eng Part C Methods.* 2015 Jan;21(1):77-87. doi: 10.1089/ten.tec.2013.0666.
64. Bondioli E, Fini M, Veronesi F, et al. Development and evaluation of a decellularized membrane from human dermis. *J Tissue Eng Regen Med.* 2014;8(4):325-336. doi: 10.1002/term.1530.
65. Elder B, Eleswarapu S, Athanasiou K. Extraction techniques for the decellularization of tissue-engineered articular cartilage constructs. *Biomaterials.* 2009;30(22):3749-3756. doi: 10.1016/j.biomaterials.2009.03.050.
66. Cox B, Emili A. Tissue subcellular fractionation and protein extraction for use in mass-spectrometry based proteomics. *Nat Protoc.* 2006;1(4):1872-1878. doi: 10.1038/nprot.2006.273.
67. Woods T, Gratzner P. Effectiveness of three extraction techniques in the development of a decellularized bone-anterior cruciate ligament-bone graft. *Biomaterials.* 2005;26(35):7339-7349. doi: 10.1016/j.biomaterials.2005.05.066.
68. Galili U. The alpha-gal epitope and the anti-Gal antibody in xenotransplantation and in cancer immunotherapy. *Immunol Cell Biol.* 2005;6(83):674-686. doi: 10.1111/j.1440-1711.2005.01366.
69. Crapo P, Gilbert T, Badylak S. An overview of tissue and whole organ decellularization processes. *Biomaterials.* 2011;32(12):3233-3243. doi: 10.1016/j.biomaterials.2011.01.057.
70. Kasimir M, Rieder E, Seebacher G, et al. Comparison of different decellularization procedures of porcine heart valves. *Int J Artif Organs.* 2003;26(5):421-427. doi: 10.1177/039139880302600508.
71. Groeber F, Holeiter M, Hampel M, Hinderer S, Schenke-Layland K. Skin tissue engineering *in vivo* and *in vitro* applications. *Adv Drug Deliv Rev.* 2011;63(4-5):352-366. doi: 10.1016/j.addr.2011.01.005.
72. Funamoto S, Nam K, Kimura T, et al. The use of high hydrostatic pressure treatment to decellularize blood vessels. *Biomaterials.* 2010;31(13):3590-3595. doi: 10.1016/j.biomaterials.2010.01.073.
73. Kheir E, Stapleton T, Shaw D, Jin Z, et al. Development and characterization of an acellular porcine cartilage bone matrix for use in tissue engineering. *J Biomed Mater Res A.* 2011;99(2):283-294. doi: 10.1002/jbm.a.33171.
74. Morris A, Chang J, Kyriakides T. Inadequate processing of decellularized dermal matrix reduces cell viability *in vitro* and increases apoptosis and acute inflammation *in vivo.* *Biores Open Access.* 2016;5(1):177-187. doi: 10.1089/biores.2016.0021.
75. Luo X, Kulig K, Finkelstein E, et al. *In vitro* evaluation of decellularized ECM-derived surgical scaffold biomaterials. *J Biomed Mater Res B Appl Biomater.* 2017;105(3):585-593. doi: 10.1002/jbm.b.33572.
76. Vavken P, Joshi S, Murray MM. Triton-x is most effective among three decellularization agents for tissue engineering. *J Orthop Res.* 2009 Dec;27(12):1612-1618. doi: 10.1002/jor.20932.
77. Rieder E, Kasimir M, Silberhumer G, et al. Decellularization protocols of porcine heart valves differ importantly in efficiency of cell removal and susceptibility of the matrix to recellularization with human vascular cells. *J Thorac Cardiovasc Surg.* 2004;127(2):399-405. doi: 10.1016/j.jtcvs.2003.06.017.
78. Hogg P, Rooney P, Ingham E, et al. Development of a decellularized dermis. *Cell Tissue Bank.* 2013;14:465-474. doi: 10.1007/s10561-012-9333-1.
79. Stapleton T, Ingram J, Fisher J, Ingham E. Investigation of the regenerative capacity of an acellular porcine medial meniscus for tissue engineering applications. *Tissue Eng Part A.* 2011;17(1-2):231-42. doi: 10.1089/ten.TEA.2009.0807.
80. Vittekova M, Draganova J, Kabat P, et al. Cytotoxicity testing of scaffolds potentially suitable for the preparation of three-dimensional skin substitutes. *Cell Tissue Bank.* 2014;15:345-355. doi: 10.1007/s10561-013-9390-0.
81. Wang Q, Zhang C, Zhang L, et al. The preparation and comparison of decellularized nerve scaffold of tissue engineering. *J Biomed Mater Res A.* 2014;102(12):4301-4308. doi: 10.1002/jbm.a.35103.
82. Wilshaw S-P, Kearney J, Fisher J, et al. Production of an acellular amniotic membrane matrix for use in tissue engineering. *Tissue Eng.* 2006;12(8):2117-2129. doi: 10.1089/ten.2006.12.2117.
83. O'Brien F. Biomaterials & scaffolds for tissue engineering. *Materials Today.* 2011;14(3):88-95. [https://doi.org/10.1016/S1369-7021\(11\)70058-X](https://doi.org/10.1016/S1369-7021(11)70058-X).
84. Ren H, Shi X, Tao L, et al. Evaluation of two decellularization methods in the development of a whole-organ decellularized rat liver scaffold. *Liver Int.* 2013 Mar;33(3):448-58. doi: 10.1111/liv.12088. doi: 10.1111/liv.12088.

Authors' ORCID iDs and academic degrees:

Olga Macagonova, MD, PhD, Scientific Researcher – <https://orcid.org/0000-0003-4414-31966>

Doina Risnic, MD, Undergraduate – <https://orcid.org/0000-0002-8142-4467>

Adrian Cociug, MD, PhD, MD, Scientific Researcher – <https://orcid.org/0000-0001-5878-0239>

Viorel Nacu, MD, PhD, MPH, Professor – <https://orcid.org/0000-0003-2274-9912>

Authors' contribution

MO and DR proposed the concept and design of the study, selected the literature and contributed to the elaboration and writing of the manuscript text. CA and NV performed a critical analysis and helped draft the manuscript. The approval of the final version of the manuscript was read and confirmed by all the authors.

Funding

This study was supported by Nicolae Testemitanu State University of Medicine and Pharmacy, and the research project “Nanoarhitecturi în bază de GaN și matrici tridimensionale din materiale biologice pentru aplicații în microfluidică și inginerie tisulară” [GaN-based nanoarchitectures and three-dimensional matrices of biological materials for applications in microfluidics and tissue engineering] – 20.80009.5007.20 offered by the National Agency for Research and Development of the Government of the Republic of Moldova.

Conflict of interests

The authors declare the absence of a conflict of financial or non-financial interests.